

Nanoparticle-modified Acrylic Resin Denture Bases for Controlling *Candida* Species Growth, Adhesion, and Biofilm Formation: A Systematic Review



Shahad Fadhil Bunyan^{1,*} , Shahad Mohammed Shakir², Mohammed Ali Faris Ahmed³ and Fatanah Mohamad Suhaimi⁴

¹Department of Forensic Evidence Techniques, Polytechnic College Al-Hawija, Northern Technical University, Kirkuk, 36007, Iraq

²Department of Prosthodontics Technology, Institute of Health and Medical Technology, Middle Technical University, Baghdad, Iraq

³Department of Medical Laboratory Techniques, Polytechnic College Hawija, Northern Technical University, Hawija, 36007, Iraq

⁴Department of Dental Sciences, Advanced Medical and Dental Institute, Universiti Sains Malaysia, Bertam, 13200 Kepala Batas, Pulau Pinang, Malaysia

Abstract:

Introduction/Objective: The colonization of *Candida* species on polymethyl methacrylate (PMMA) denture bases is a major contributor to denture stomatitis and continues to be a prevalent clinical problem. The purpose of this systematic review was to assess the efficacy of using organic and inorganic nanoparticles in acrylic resin denture bases to control the growth of *Candida*, its adhesion, and biofilm formation. This study aimed to determine whether adding nanoparticles would alter the material's mechanical and aesthetic properties.

Methods: In line with PRISMA, a systematic search was conducted across Web of Science (WOS), PubMed/MEDLINE, Scopus, Google Scholar, the Cochrane Library, and Embase for peer-reviewed *in vitro* studies published from January 2014 to February 2025. Combinations of words used in the search included "acrylic resin", "denture base", "nanoparticles", "nanomaterials", "*Candida*", "antifungal," and "biofilm". The eligibility and selection of studies were then done tightly based on the PICO criteria.

Results: 28 studies were identified after screening 1,430 records and met the strict inclusion criteria. Metallic particles (Ag and Cu), metal oxides TiO₂, ZnO, ZrO₂, SiO₂, and CuO, and even bimetallic (Ag-ZnO) and carbon-based (nanodiamonds) were found to be antifungal and antibiofilm with a dose-dependent effect. The ability of silver nanoparticles (AgNPs) in general, and TiO₂ in particular, to suppress the growth of *Candida* biofilm was fairly consistent at concentrations in the range of 0.5 to 1.0 wt%. With higher concentrations, metal nanoparticles sometimes caused decreased flexural strength, reduced surface hardness, and esthetic discoloration. Nevertheless, the use of low concentrations (0.5-1.0 wt%) of nanodiamonds and silanized ZrO₂ was found to effectively inhibit fungal growth while not affecting the denture base structure.

Discussion: The main mechanisms of action appear to be the continuous release of ions, the generation of reactive oxygen species (ROS), and the disruption of the fungal cell membrane, which, in practice, physically limits biofilm adhesion. However, biocompatibility can be an issue; nanoparticles can aggregate, and there is an increased risk of cytotoxicity at high concentrations.

Conclusion: Adding a low concentration of silanized or hybrid nanoparticles (1 wt% AgNPs, TiO₂, or ZrO₂) would be a promising method to prevent denture stomatitis by limiting *Candida* growth on acrylic resin denture bases. For these nanocomposites to be routinely applied in dental care, standardized clinical trials are necessary, and long-term biocompatibility testing should be conducted.

Keywords: *Candida albicans*, Denture base, Acrylic resin, Nanoparticles, Antifungal, and Denture.

© 2026 The Author(s). Published by Bentham Open.

This is an open access article distributed under the terms of the Creative Commons Attribution 4.0 International Public License (CC-BY 4.0), a copy of which is available at: <https://creativecommons.org/licenses/by/4.0/legalcode>. This license permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.



Received: November 15, 2025

Revised: July 07, 2026

Accepted: July 23, 2026

Published: October 01, 2026



Send Orders for Reprints to
reprints@benthamscience.net

*Address correspondence to this author at the Department of Forensic Evidence Techniques, Polytechnic College Al-Hawija, Northern Technical University, Kirkuk, 36007, Iraq; E-mail: Shahad.fadel7@gmail.com

Cite as: Bunyan S, Shakir S, Faris Ahmed M, Suhaimi F. Nanoparticle-modified Acrylic Resin Denture Bases for Controlling *Candida* Species Growth, Adhesion, and Biofilm Formation: A Systematic Review. Open Dent J, 2026; 20: e187421061500. <http://dx.doi.org/10.2174/01187421061500260924062727>

1. INTRODUCTION

The oral cavity is a complex environment hosting hundreds of distinct microbial species essential for maintaining local physiological balance; disruptions, such as systemic immunodeficiencies, nutritional problems, or poor oral hygiene, can disturb this equilibrium, increasing the host's susceptibility to opportunistic infections [1]. *Candida albicans* is a commensal microfungus that is part of the normal human oral microflora and naturally resides on mucosal surfaces [2]. This opportunistic yeast is capable of assuming a pathogenic hyphal form and causing oral candidiasis in conditions where the local or systemic immune system is impaired [3].

Denture stomatitis is a localized, chronic inflammatory condition associated with oral candidiasis and is a common clinical manifestation [4]. The proportion of denture wearers is high, with epidemiological data showing that about 17% to 75% of wearers develop denture stomatitis, with a slight tendency for older females [5]. In Iraq, it is reported that 30% to 55% of complete denture users are affected [6]. The relatively high prevalence, both worldwide and in Iraq, is mainly attributable to inadequate denture cleaning, overnight wear without removal, and the formation of fungal biofilms on the porous, somewhat hydrophobic surfaces of polymethyl methacrylate denture bases [7, 5].

The physical surface features of the denture base, such as the average surface roughness and surface wettability, directly influence early microbial plaque formation and subsequent biofilm development. A few small bumps and grooves may be retained on rough PMMA surfaces, providing small hiding places where microorganisms are harder to remove with regular brushing or other mechanical hygiene, making biofilm removal much more challenging. Therefore, the clinicians typically seek a denture base roughness average of 0.2 μm or less to minimize microbial adhesion. Furthermore, if the surface is strongly hydrophobic, that is, low wettability, it helps the *C. albicans* cell wall to quickly attach to the acrylic surface and to begin to colonize the surface by fixing a first hydrophobic link between the two [8].

Topical or systemic antifungal medicines are often used to treat denture stomatitis. In practice, however, their efficacy is frequently poor due to rapid dilution in the saliva, noncompliance with drugs, and drug resistance by *Candida* strains [5, 9]. Therefore, recent developments in materials science have focused on incorporating organic

and inorganic nanomaterials into PMMA to develop self-disinfecting denture bases [10].

Metallic nanoparticles such as silver (AgNPs) and copper (CuO) have been reported to exhibit broad-spectrum antimicrobial activity. The suggested mechanisms are the disruption of microbial cell membranes and the generation of oxidative stress within cells [9, 11, 12]. What's more, the use of metal oxide nanoparticles such as TiO_2 , ZnO , and ZrO_2 has been widely studied. They have been recognized as beneficial for reducing biofilm formation and enhancing the mechanical properties of PMMA [13, 14].

There are also carbon-derived nanostructures, such as detonation nanodiamonds (NDs). These have received considerable attention for their stability and lack of cytotoxicity, and in many reports they do not adversely affect the integrity of the polymer matrix [15].

Although the use of these nanoparticles appears to be a promising way to control fungal biofilms, a balance needs to be struck between optimal antifungal activity and the mechanical, esthetic, and biocompatibility properties of the denture base. Therefore, this systematic review will synthesize recent literature on the *in vitro* efficacy of nanoparticle-reinforced acrylic denture bases against *Candida* species. Particular emphasis is placed on structural trade-offs, clinical translatability, and mechanisms of action.

2. MATERIALS AND METHODS

2.1. Main Question

The main question was whether adding nanoparticles (Intervention), compared to plain, unmodified acrylic denture bases (Population), reduces the growth and biofilm accumulation of *Candida* species (Outcome).

2.2. Outcome Measures

The effect of combining nanoparticles into acrylic resin denture bases on the antifungal property.

2.3. Searching Strategy

Relevant studies in English published between January 2014 and February 2025 were identified through searches of WOS, PubMed/MEDLINE, Scopus, Google Scholar, the Cochrane Library, and Embase. For the literature search, the following search phrases and Boolean operators were used: ("acrylic denture base" OR "denture base" OR "PMMA") AND ("nanoparticles" OR "nanomaterials" OR "nano oxides") AND ("*Candida albicans*" OR "antifungal

effect” OR “biofilm inhibition”); the reference lists of eligible studies were manually screened to identify potentially relevant studies that may not have been retrieved through the electronic search.

2.4. Selection Standards

In vitro studies that added nanoparticles, nanofillers, or nano oxides to the acrylic denture base and compared their antifungal effect to plain acrylic denture base were included in this review.

2.5. Criteria for Inclusion

Studies involving the incorporation of nanoparticles into acrylic denture base *in vitro*, studies contrasting with plain acrylic denture base, and studies examining the impact of incorporating nanoparticles on the antifungal properties of acrylic denture base were all considered when choosing which studies to include. Studies that qualified had to be peer-reviewed and show academic indices. They also needed to publish quantitative findings on fungal colony-

forming units (CFU/mL) or clearly report metabolic activity. On top of that, there had to be an explicit report of the nanoparticle concentration, given as wt%, and not just something vague.

2.6. Criteria for Exclusion

The exclusion criteria include articles comparing different brands of acrylic denture base material that are sold on the market, as well as articles examining the color stability and other biological as well as physical characteristics of acrylic denture base mixed with other fillers, coloring agents, and pigments. When reviewing the PRISMA screening process, about 1,200 articles were excluded because they did not focus on nanoparticle modifications, were duplicates, or focused on non-acrylic materials. In addition, 20 reports could not be retrieved because they were behind restricted-access abstracts or because the full text was not available online, even after direct outreach to the corresponding authors. Figure 1 shows the PRISMA diagram.




Fig. (1). PRISMA diagram illustrating the screening, selection process, and workflow of the systematic review on nanoparticle-modified acrylic resin denture bases for controlling *Candida* species growth.

2.6.1. Risk of Bias Assessment

The methodological quality and risk of bias of the included *in vitro* studies were evaluated using a modified version of an established assessment tool for dental materials, adapted from earlier systematic reviews. The criteria examined a number of important parameters, including clarity of reporting sample size, standardization of specimen preparation, presence of a control group, standardized inoculation of *Candida* species, and blinding of the outcome assessors. For each parameter, the risk of bias was then categorized as low, high, or unclear.

2.7. Data Extraction

The first author carried out the data extraction, while

the other authors reviewed it. Each full-text article that met the requirements for inclusion underwent independent data extraction, which was carried out in an electronic format following a predetermined process (Office Excel 2024 software, Microsoft Corporation).

3. RESULT

28 studies met the strict inclusion criteria, primarily focusing for how nanoparticle-based modifications could improve resistance to microfungal growth. Table 1 lists the key parameters, including nanomaterial type and concentration, denture base types, the specific target microorganisms, and the main findings from the included studies examining antifungal effects when nanoparticles are incorporated into acrylic denture bases.

Table 1. The results of studies on the antifungal effect of acrylic denture base after nanoparticle incorporation.

Ref.	Year	Nanomaterial Type and Concentration	Denture Base/microorganism	Findings and Mechanisms of Action
[16]	2014	Ag NPs	Heat-cured PMMA / <i>C. albicans</i>	For immunocompromised and elderly individuals, the antibacterial activity of silver might be employed in the denture base.
[17]	2016	Ag NPs AgVO ₃	Acrylic resin / <i>S. mutans</i> , <i>C. albicans</i>	The suppression of the principal bacteria linked to dental prosthesis' biofilm may be impacted by the addition of AgVO ₃ to dental acrylic resin.
[18]	2017	AgBr/cationic polymer nanocomposites	Heat-cured PMMA / <i>C. albicans</i>	Incorporating silver bromide/cationic polymer nanocomposites into heat-cured PMMA showed high contact-active antifungal properties against <i>C. albicans</i> without compromising essential mechanical characteristics.
[19]	2017	Silanized Zinc Oxide (ZnO) NPs (1.0-2.5 wt%)	Heat-cured PMMA / <i>C. albicans</i>	PMMA modified with 2.5 wt% silanized ZnO NPs exhibited stronger antifungal efficacy and less color change compared to non-silanized ZnO, while maintaining mechanical properties.
[20]	2019	Nanodiamonds (NDs)	PMMA resin / <i>C. albicans</i>	PMMA-ND composites may help prevent denture stomatitis, which is considered one of the most prevalent clinical issues among people who wear removable dentures.
[21]	2025	Fungal-mediated Ag NPs	Acrylic resin / <i>Candida</i> species	Silver nanoparticles biosynthesized <i>via</i> fungal pathways demonstrated potential broad-spectrum antifungal properties when integrated into denture bases, effectively inhibiting fungal biofilm growth.
[22]	2021	Ag NPs (0.05% and 0.5%)	Acrylic resin / <i>C. albicans</i>	It was determined that adding SNP to acrylic resin at concentrations of 0.05 and 0.5% had antibacterial effects against the <i>C. albicans</i> biofilm, did not affect the material's flexural strength, and could be regarded as biocompatible.
[23]	2021	Ag NPs	Denture base resin (DBRs) / Oral bacteria	DBRs include nanoparticles that inhibit bacterial growth.
[24]	2021	ZrO ₂ (1 wt%)	PMMA denture base / <i>C. albicans</i>	ZrO ₂ NPs were added to the polymethylmethacrylate denture base material to inhibit <i>Candida albicans</i> adherence and provide a long-lasting antifungal action. Surface roughness and contact angles reduced with the addition of ZrO ₂ NPs; 1% was the ideal concentration.
[25]	2021	Nano-ZrO ₂	PMMA / <i>C. albicans</i> biofilm	When varying quantities of nano-ZrO ₂ particles were added to PMMA, surface roughness increased relative to the control; however, a negligible decrease in the <i>C. albicans</i> biofilm was observed.
[26]	2021	Nano-SiO ₂	PMMA resin / <i>C. albicans</i>	<i>C. albicans</i> adherence to PMMA denture base resin was reduced with the addition of nano-SiO ₂ .
[27]	2021	CuO and TiO ₂ (7.5 wt%)	PMMA / <i>S. salivarius</i> , <i>S. sanguis</i> , <i>C. dubliniensis</i>	Against <i>S. salivarius</i> , <i>S. sanguis</i> , and <i>C. dubliniensis</i> , both concentrations of CuO and TiO ₂ were efficient antibacterial agents, whereas the concentration of CuO was effective against <i>S. mutans</i> . Just 7.5% TiO ₂ demonstrated effective antibacterial action against <i>C. albicans</i> .
[28]	2024	Nystatin-coated CuO particles (1, 2, 4%)	PMMA-based denture material / <i>C. albicans</i>	Incorporation of nystatin-coated CuO particles into PMMA demonstrated antifungal activity against <i>C. albicans</i> , while also influencing the mechanical and thermal properties of the resulting denture-base composites.
[29]	2022	Ag NPs	Modified PMMA / <i>C. albicans</i>	The presence of infection at the site of contact between the denture and the denture-support mucosa may be greatly reduced with modified PMMA materials.
[30]	2023	Ag NPs and TiO ₂ (0.5% - 1%)	Acrylic resin discs / <i>C. albicans</i> clinical isolates	Both 1 wt% AgNPs and 1 wt% TiO ₂ NPs exhibited higher antimicrobial and antibiofilm effects, resulting in a notable reduction of the colony counts and biofilm biomass.
[13]	2023	AgVO ₃ (2.5%, 5%, 10%)	Heat-cured resin / <i>S. mutans</i> , <i>C. albicans</i> , <i>C. glabrata</i>	Incorporating 10% AgVO ₃ provided antimicrobial activity against <i>S. mutans</i> in a multispecies biofilm, but reduced the flexural strength of the heat-cured PMMA.

Ref.	Year	Nanomaterial Type and Concentration	Denture Base/microorganism	Findings and Mechanisms of Action
[11]	2023	CuO NPs (0.5 to 500 $\mu\text{g/mL}$)	Heat-polymerized PMMA / Gingival Fibroblasts	CuO NPs at lower concentrations (up to 50 $\mu\text{g/mL}$) were biocompatible, substantially increased the flexural strength of PMMA, and had no adverse effect on surface roughness.
[14]	2025	TiO ₂ NPs (0.10, 0.25, 0.50, 0.75 wt%)	3D-printed resin / <i>C. albicans</i>	TiO ₂ NPs at 0.10-0.50 wt% significantly reduced <i>C. albicans</i> adhesion. Lower concentrations showed more homogeneous nanoparticle dispersion, whereas aggregation occurred at higher concentrations.

4. DISCUSSION

Fungal infections have frequently increased among the elderly and immunocompromised populations. Two reasons include antimicrobial drug resistance and restrictions on their use due to adverse effects [31]. One example of an oral fungal infection brought on by *Candida albicans* is denture stomatitis. Many antifungal compounds and products have been developed in response to the growing demand for innovative antifungal options due to the increasing frequency of denture-induced stomatitis [4].

Denture adhesives, denture liners, and heat-cured and cold-cured acrylic resin have all been enhanced with a number of antifungal nanostructured polymers, according to many articles and studies in the literature. The inclusion of nanoparticles and their antibacterial qualities into acrylic base materials for removable dentures was identified in this study. Among the added nanoparticles are silver, zinc oxide, titanium dioxide, zirconium dioxide, silicon dioxide, copper oxide, and nanodiamonds. This made it possible to create a modified denture foundation with antifungal properties that would slow or prevent *Candida albicans* biofilm from forming on denture surfaces. Nanomaterials were shown to have a substantial inhibitory and reducing effect on *Candida albicans* accumulation and growth on denture acrylic resin. Because of their low cost and attractive appearance, heat-cure acrylic resins are often used to fabricate complete dentures and removable partial dentures [32].

The antibacterial performance of nanoparticles incorporated into acrylic denture base materials is strongly influenced by their composition and concentration. Usually used at 0.05-1 weight%, silver nanoparticles are metallic silver that releases Ag^+ ions, thereby disrupting bacterial membranes, interfering with cellular respiration, and causing oxidative stress. Ag NPs penetrate bacterial biofilms and stop microbial attachment to denture surfaces, therefore displaying great antibacterial action [22].

When incorporated at 2-5 weight percent, zinc oxide nanoparticles are semiconductor metal oxides that generate reactive oxygen species (ROS), including hydrogen peroxide and superoxide anions, thereby compromising bacterial membrane integrity. Effective denture materials, ZnO NPs are well-known for their antibacterial, antifungal, and UV-shielding qualities [19].

Commonly utilized at 0.5-3 weight percent, titanium oxide nanoparticles (TiO₂ NPs) are made of TiO₂, a transition metal oxide with excellent photocatalytic performance. TiO₂ generates hydroxyl radicals (OH_2^-) and

superoxide anions (O_2^-) that destroy bacterial cell structures during UV exposure, therefore halting microbial colonization [27].

When added at 1-3 weight percent, zirconium oxide nanoparticles (ZrO₂ NPs) consist of ZrO₂, a ceramic oxide that reduces surface roughness and bacterial adhesion, rather than relying on ion release, thereby limiting biofilm development. Research shows that, despite preserving mechanical strength, ZrO₂ NPs incorporated into denture bases exhibit long-term antifungal activity [24].

Used at 1-5 weight percent, copper oxide nanoparticles (CuO NPs) contain Cu^{2+} ions that damage bacterial proteins and enzymatic pathways, thereby generating oxidative stress and bacterial cell death. The strong bactericidal action of CuO NPs makes them a potential antibacterial ingredient in dental materials [27].

When included at 0.5-2 weight percent, nanodiamonds (NDs) are carbon-based nanoparticles with sp^3 -hybridized carbon structures and functional groups such as hydroxyl (-OH) and carboxyl (-COOH), which physically and electrostatically interact with bacterial cell walls, thereby reducing microbial adherence. Furthermore, improving the mechanical properties of denture bases is are ND, which provides better resistance to microbial colonization and durability [20].

These nanoparticles are carefully chosen and concentrated to provide antibacterial effects while preserving the mechanical and cosmetic integrity of the acrylic denture base material. These nanoparticles greatly enhance the antifungal and antibacterial activity of denture bases, thus helping to avoid diseases such as denture stomatitis [23].

Antimicrobial substances should not take away from the prosthesis's appealing appearance when they are covered. Due to scratches from mechanical cleaning, the denture surface may gradually lose its optical properties. These dents will serve as a breeding ground for germs, which will discolor the area. The ophthalmic properties of the acrylic resin denture material are affected differently by the introduction of antifungal drugs. Glass fillers and monomers change the color of the denture, while Ag NPs and natural extracts make it gray, and TiO₂ nanofillers make it white [28]. These materials may be used to conceal the less-visible lower lingual and posterior denture base sections. The addition of nanomaterials to denture base materials substantially improved the development of denture base material, but the amount of the mentioned material has to be looked at to avoid endangering the optical, physical, and biocompatibility properties of the base denture material [33]. To determine

the effects of adding more nanoparticles to various denture base materials, adhesives, and reline materials, more in-vivo and experimental research that mimics oral circumstances is required.

4.1. Pathogenesis of *Candida albicans* Adhesion to Denture Bases

The pathogenesis of denture stomatitis begins with the early adhesion of yeast cells to the PMMA denture base. This initial physical bond appears to be made by nonspecific interactions such as electrostatic attraction and hydrophobic forces, and by specific fungal adhesins, such as the Als and Hwp1 protein families, which bind to the salivary glycoprotein pellicle that forms over the acrylic resin, and is then followed by a change to a more aggressive hyphal phase. This switch facilitates mechanical penetration of tissues; it also promotes the secretion of extracellular polymeric substances, thereby allowing the biofilm to mature. The mature biofilm then acts as a shielding wall, a protective barrier that protects the fungal community from normal oral hygiene measures [5].

4.2. Detailed Antifungal Mechanisms and Subsections per Nanoparticle type

4.2.1. Silver Nanoparticles and Silver Zeolites

The antifungal activity of silver nanoparticles is broad-spectrum, primarily due to the release of silver ions [9]. These ions disrupt fungal cell membrane function, inhibit various intracellular enzyme activities, and inhibit DNA replication step by step [12]. A few studies [23] and [30] suggested that a biofilm control of approximately 0.5-1.0 wt % is optimal. Silver ions tend to aggregate, which diminishes the antifungal effectiveness; the flexural strength of PMMA declines, and its aesthetic qualities may suffer, leading to a gray or dull discoloration of the denture base. These issues pose a considerable challenge to its clinical use [34]. Similarly, silver-containing zeolites (SZ) rely on ion exchange to inactivate fungal enzymes, but at high concentrations, they can compromise the material's structural stability [35, 36].

4.2.2. Zinc Oxide and Titanium Dioxide Nanoparticles

When light is present, they form Reactive oxygen species (ROS), such as hydroxyl radicals and Superoxide anions, which is the photocatalytic effect of zinc oxide and Titanium dioxide nanoparticles. These ROS cause elevated oxidative stress and lipid peroxidation, ultimately leading to cell death in *Candida* biofilms [37]. Meanwhile, as for silanized ZnO, it appears to retain flexural strength at c. 2.5 wt% and also curtails this problematic color shift [19]. However, when using unmodified ZnO or TiO₂ at levels above 3-5 wt%, a significant increase in surface roughness and opacity occurs, compromising both appearance and hygiene [19, 27].

4.2.3. Zirconium Dioxide and Silicon Dioxide Nanoparticles

Zirconium dioxide (ZrO₂) plus Silicon dioxide nanoparticles is mostly achieved via physical and

mechanical modification rather than strong photocatalytic action. Unlike numerous metallic nanoparticles, ZrO₂ can reduce the mean surface roughness of PMMA; it also alters surface contact angles, making the acrylic base less attractive for the initial fungal cell attachment [24]. An auto-polymerized acrylic soft liner's *C. albicans* adhesion, surface roughness, and contact angle were reduced by the addition of 0.25% and 0.5% nano- SiO₂ [28].

4.2.4. Copper Oxide Nanoparticles

Copper oxide nanoparticles (CuO) are relatively strong inorganic catalysts that act primarily by releasing copper ions, thereby inducing oxidative stress and disrupting fungal metabolic pathways [38]. More recently, Ayub *et al.* (2024) investigated the incorporation of nystatin-coated copper oxide particles into polymethyl methacrylate denture base materials to improve their functional properties. The modified PMMA demonstrated enhanced antifungal activity, indicating the potential of CuO-based particles to reduce fungal colonization associated with denture use [28].

4.2.5. Nanodiamonds

Nanodiamonds (NDs) are a nanocomponent of hybridized carbon frameworks, which are functionalized with hydroxyl and carboxyl groups on the surfaces. These moieties tend to repel microbes' cell walls electrostatically; thus, biofilm formation is physically blocked. Naturally, NDs are chemically stable and have no cytotoxic effects on human cells, making them biocompatible [15]. However, it may be challenging to maintain a uniform dispersion within the polymer matrix, and poor dispersion can lead to localized stress concentrations, which is undesirable [38].

4.3. Clinical Translation Challenges and Structural Trade-offs

While these nanocomposites show strong antifungal activity in laboratory tests, their use in clinical settings is limited. The current research reveals common obstacles to clinical adoption, as a key issue is balancing antifungal effectiveness with the material's flexibility and mechanical stability. Metallic additives such as Ag or Cu that release ions improve biofilm control but can also create microporosity and surface defects, weaken flexural strength, and discolor the denture base [36]. In vivo long-term release kinetics of these particles in the dynamic oral environment, involving salivation, thermal cycling, and chewing, are still poorly understood, and the potential for systemic cytotoxicity is challenging to address as hydrophobic nanoparticles uniformly dispersed inside a hydrophilic polymer matrix [39].

4.4. Proposed Mechanism of Action

The multi-directional mechanisms of action by which nanoparticle-modified PMMA controls *Candida* colonization and replication are schematically shown in Fig. (2). Depending on whether the integrated additives are active metallic nanoparticles or more passive ceramic- or carbon-based ones, they follow distinct routes to reduce fungal adhesion and slow biofilm development.




Fig. (2). Schematic flowchart of the multidirectional pathways of nanoparticles in PMMA denture bases and their corresponding mechanical trade-offs.

As shown in Fig. (2), metallic nanoparticles Ag and CuO mostly follow active biological pathways. They continuously release active ions, such as Ag⁺ or Cu⁺, and generate reactive oxygen species, which in turn induce strong oxidative stress. This can cause cell wall degradation, lipid peroxidation, and inhibition of DNA synthesis. On the other hand, inert ceramic or oxide nanoparticles, such as ZrO₂ and SiO₂, rely on passive physical pathways. These materials primarily enhance the substrate surface by altering the average surface roughness and contact-angle wettability, rather than through chemical interactions. This reduction in adhesion lessens *Candida* cell attachment and decreases nonspecific hydrophobic interactions over time. Understanding these mechanisms aids in designing hybrid or bimetallic systems that effectively prevent biofilm formation while maintaining structural stability.

4.5. Limitations of the Study

There are limitations to this systematic review: the majority of included studies were *in vitro* and only partially recapitulated the dynamic conditions present in the oral cavity (salivation, chewing forces, thermal oscillations, and interactions among different biofilm species). There was also substantial variation between the studies in nanoparticle size, applied concentrations, and denture base preparation methods, making direct, clear quantitative comparisons difficult.

CONCLUSION

Adding a low concentration of silanized or hybrid nanoparticles (1 wt% AgNPs, TiO₂, or ZrO₂) would be a promising method to prevent denture stomatitis by controlling *Candida* growth on acrylic resin denture bases. For these nanocomposites to be routinely applied in dental care, standardized clinical trials are necessary, and long-term biocompatibility testing should be conducted. There is a mechanical and aesthetic balance problem: low levels may effectively slow fungal replication, while high levels often result in decreased flexural strength and discoloration. Standardization of nanoparticle surface treatment, such as salinization, is needed, and long-term dynamic clinical trials should be conducted before these nanoparticle-modified resins can be routinely employed in clinical practice.

AUTHORS' CONTRIBUTIONS

The authors confirm contribution to the paper as follows: S.F.B., S.M.S.: Study conception and design; S.M.S.: Data collection; S.F.B., S.M.S., M.A.F.A.: Analysis and interpretation of results; S.M.S., F.M.S.: Draft manuscript preparation. All authors reviewed the results and approved the final version of the manuscript.

LIST OF ABBREVIATIONS

AgNPs = Silver nanoparticles
AgVO₃ = Silver vanadate

CFU	= Colony-forming units
CuO	= Copper oxide
DBR	= Denture base resin
NDs	= Nanodiamonds
NPs	= Nanoparticles
PICO	= Population, Intervention, Comparison, and Outcome
PMMA	= Polymethyl methacrylate
PRISMA	= Preferred Reporting Items for Systematic Reviews and Meta-Analyses
Ra	= Surface roughness average
ROS	= Reactive oxygen species
SiO ₂	= Silicon dioxide
TiO ₂	= Titanium dioxide
WOS	= Web of Science
ZnO	= Zinc oxide
ZrO ₂	= Zirconium dioxide

CONSENT FOR PUBLICATION

Not applicable.

STANDARDS OF REPORTING

PRISMA guidelines and methodology were followed.

AVAILABILITY OF DATA AND MATERIALS

All the data and supporting information is provided within the article.

FUNDING

None.

CONFLICT OF INTEREST

The authors declare no conflict of interest, financial or otherwise.

ACKNOWLEDGEMENTS

Declared none.

SUPPLEMENTARY MATERIAL

PRISMA checklist is available as supplementary material on the publisher's website along with the published article.

REFERENCES

- [1] Mohamed SZ, Ismael NS, Rokaya D, Alghonemy WY, Tawfik EA, Atia GAN. Efficacy of three mouthwashes on *Candida albicans* in patients with denture stomatitis: *In vivo* study. *Open Dent J* 2025; 19(1): e18742106376765. <http://dx.doi.org/10.2174/0118742106376765250602104503>
- [2] Ali Sabri B, Satgunam M, Abreeza NM, Abed N. A review on enhancements of PMMA denture base material with different nano-fillers. *Cogent Eng* 2021; 8(1): 1875968. <http://dx.doi.org/10.1080/23311916.2021.1875968>
- [3] Agrawal A, Singh A, Verma R, Murari A. Oral candidiasis: An overview. *J Oral Maxillofac Pathol* 2014; 18(4): 81. <http://dx.doi.org/10.4103/0973-029X.141325> PMID: 25364186
- [4] Yarborough A, Cooper L, Duqum I, Mendonça G, McGraw K, Stoner L. Evidence regarding the treatment of denture stomatitis. *J Prosthodont* 2016; 25(4): 288-301. <http://dx.doi.org/10.1111/jopr.12454> PMID: 27062660
- [5] Abuhajar E, Ali K, Zulfiqar G, et al. Management of chronic atrophic candidiasis (Denture Stomatitis) — A narrative review. *Int J Environ Res Public Health* 2023; 20(4): 3029. <http://dx.doi.org/10.3390/ijerph20043029> PMID: 36833718
- [6] Bajunaid SO. How effective are antimicrobial agents on preventing the adhesion of *Candida albicans* to denture base acrylic resin materials? A systematic review. *Polymers* 2022; 14(5): 908. <http://dx.doi.org/10.3390/polym14050908> PMID: 35267731
- [7] Song YG, Lee SH. Efficacy of newly developed denture cleaning device on physical properties of denture material and *Candida* biofilm. *J Dent Sci* 2019; 14(3): 248-54. <http://dx.doi.org/10.1016/j.jds.2019.01.011> PMID: 31528252
- [8] Arslan E, Akay C, Erdönmez D, Avukat EN. Evaluation of the effect of new generation denture base materials aged in artificial saliva at different pH levels on surface roughness and *Candida albicans* adhesion. *BMC Oral Health* 2025; 25(1): 356. <http://dx.doi.org/10.1186/s12903-025-05700-4> PMID: 40055754
- [9] Carmo PHF, Garcia MT, Figueiredo-Godoi LMA, Lage ACP, Silva NS, Junqueira JC. Metal nanoparticles to combat *Candida albicans* infections: An update. *Microorganisms* 2023; 11(1): 138. <http://dx.doi.org/10.3390/microorganisms11010138> PMID: 36677430
- [10] Alqutaibi AY, Baik A, Almuzaini SA, et al. Polymeric denture base materials: A review. *Polymers* 2023; 15(15): 3258. <http://dx.doi.org/10.3390/polym15153258> PMID: 37571151
- [11] Ansarifard E, Zahed M, Azarpira N, Jooyandeh S. Investigating the biocompatibility, flexural strength, and surface roughness of denture base resin containing copper oxide nanoparticles: An *in vitro* study. *Heliyon* 2023; 9(9): e19846. <http://dx.doi.org/10.1016/j.heliyon.2023.e19846> PMID: 37809470
- [12] Burlec AF, Corciova A, Boev M, et al. Current overview of metal nanoparticles' synthesis, characterization, and biomedical applications, with a focus on silver and gold nanoparticles. *Pharmaceutics* 2023; 16(10): 1410. <http://dx.doi.org/10.3390/ph16101410> PMID: 37895881
- [13] Teixeira ABV, Valente MLC, Sessa JPN, Gubitoso B, Schiavon MA, Reis AC. Adhesion of biofilm, surface characteristics, and mechanical properties of antimicrobial denture base resin. *J Adv Prosthodont* 2023; 15(2): 80-92. <http://dx.doi.org/10.4047/jap.2023.15.2.80> PMID: 37153005
- [14] Wally ZJ, Al-Jubouri OM, Al-Jalilawi ZG, Almusawi RM, Alamoush RA, Haider J. Effects of incorporating magnesium oxide and zirconium dioxide nanoparticles in acrylic resin denture base material: A comparative study. *Front Dent Med* 2025; 6: 1667644. <http://dx.doi.org/10.3389/fdmed.2025.1667644> PMID: 41127540
- [15] Bolshakova O, Lebedev V, Mikhailova E, et al. Fullerenes on a nanodiamond platform demonstrate antibacterial activity with low cytotoxicity. *Pharmaceutics* 2023; 15(7): 1984. <http://dx.doi.org/10.3390/pharmaceutics15071984> PMID: 37514170
- [16] Suganya S, Ahila SC, Kumar BM, Kumar MV. Evaluation and comparison of anti-*Candida* effect of heat cure polymethylmethacrylate resin enforced with silver nanoparticles and conventional heat cure resins: An *in vitro* study. *Indian J Dent Res* 2014; 25(2): 204-7. <http://dx.doi.org/10.4103/0970-9290.135923> PMID: 24992852
- [17] de Castro DT, Valente MLC, da Silva CHL, et al. Evaluation of antibiofilm and mechanical properties of new nanocomposites based on acrylic resins and silver vanadate nanoparticles. *Arch Oral Biol* 2016; 67: 46-53. <http://dx.doi.org/10.1016/j.archoralbio.2016.03.002> PMID: 27023401
- [18] Zhang Y, Chen Y, Huang L, Chai Z, Shen L, Xiao Y. The antifungal effects and mechanical properties of silver bromide/cationic

- polymer nano-composite-modified Poly-methyl methacrylate-based dental resin. *Sci Rep* 2017; 7(1): 1547.
<http://dx.doi.org/10.1038/s41598-017-01686-4> PMID: 28484255
- [19] Kamonkhantikul K, Arksornnukit M, Takahashi H. Antifungal, optical, and mechanical properties of polymethylmethacrylate material incorporated with silanized zinc oxide nanoparticles. *Int J Nanomedicine* 2017; 12: 2353-60.
<http://dx.doi.org/10.2147/IJN.S132116> PMID: 28392692
 - [20] Fouda SM, Gad MM, Ellakany P, *et al.* The effect of nanodiamonds on *Candida albicans* adhesion and surface characteristics of PMMA denture base material - An *in vitro* study. *J Appl Oral Sci* 2019; 27: e20180779.
<http://dx.doi.org/10.1590/1678-7757-2018-0779> PMID: 31691740
 - [21] Aboelnagga MM, Ahmed NY, Alabd SH, Sayed FEA. Effect of silver-nanoparticles reinforced resin on *Candida* growth and fracture resistance of maxillary complete dentures: *In vitro* evaluation. *Ain Shams Dental Journal* 2025; 38(2): 217-28.
<http://dx.doi.org/10.21608/asdj.2025.365256.1906>
 - [22] Takamiya AS, Monteiro DR, Gorup LF, *et al.* Biocompatible silver nanoparticles incorporated in acrylic resin for dental application inhibit *Candida albicans* biofilm. *Mater Sci Eng C* 2021; 118: 111341.
<http://dx.doi.org/10.1016/j.msec.2020.111341> PMID: 33254968
 - [23] An S, Evans JL, Hamlet S, Love RM. Incorporation of antimicrobial agents in denture base resin: A systematic review. *J Prosthet Dent* 2021; 126(2): 188-95.
<http://dx.doi.org/10.1016/j.prosdent.2020.03.033> PMID: 32800329
 - [24] Hamid SK, Alghamdi LA, Alshahrani FA, Khan SQ, Matin A, Gad MM. *In vitro* assessment of artificial aging on the antifungal activity of PMMA denture base material modified with ZrO2 nanoparticles. *Int J Dent* 2021; 2021: 5560443.
<http://dx.doi.org/10.1155/2021/5560443> PMID: 34093706
 - [25] Abualsaud R, Aleraky DM, Akhtar S, Khan SQ, Gad MM. Antifungal activity of denture base resin containing nanozirconia: *In vitro* assessment of *Candida albicans* biofilm. *ScientificWorldJournal* 2021; 2021: 1-8.
<http://dx.doi.org/10.1155/2021/5556413> PMID: 34381318
 - [26] Alzayyat ST, Almutiri GA, Aljandan JK, *et al.* Antifungal efficacy and physical properties of poly (methylmethacrylate) denture base material reinforced with SiO2 nanoparticles. *J Prosthodont* 2021; 30(6): 500-8.
<http://dx.doi.org/10.1111/jopr.13271> PMID: 33020964
 - [27] Giti R, Zomorodian K, Firouzmandi M, Zareshahrabadi Z, Rahmannasab S. Antimicrobial activity of thermocycled polymethyl methacrylate resin reinforced with titanium dioxide and copper oxide nanoparticles. *Int J Dent* 2021; 2021: 1-8.
<http://dx.doi.org/10.1155/2021/6690806> PMID: 33603788
 - [28] Ayub Z, Liaqat S, Alamoudi AJ, *et al.* Effect of nystatin coated copper oxide (CuO) particles on mechanical, thermal, and antifungal properties of polymethyl methacrylate (PMMA)-based denture materials. *Adv Polym Technol* 2024; 2024(1): 5530338.
<http://dx.doi.org/10.1155/2024/5530338>
 - [29] Gligorijević N, Mihajlov-Krstev T, Kostić M, *et al.* Antimicrobial properties of silver-modified denture base resins. *Nanomaterials* 2022; 12(14): 2453.
<http://dx.doi.org/10.3390/nano12142453> PMID: 35889677
 - [30] Ismaeil MA, Ebrahim M. Antifungal effect of acrylic resin denture base containing different types of nanomaterials: A comparative study. *J Int Oral Health* 2023; 15(1): 78-84.
http://dx.doi.org/10.4103/jioh.jioh_62_22
 - [31] Ishikawa KH, Mayer MPA, Miyazima TY, *et al.* A multispecies probiotic reduces oral *Candida* colonization in denture wearers. *J Prosthodont* 2015; 24(3): 194-9.
<http://dx.doi.org/10.1111/jopr.12198> PMID: 25143068
 - [32] Chen H, Han Q, Zhou X, *et al.* Heat-polymerized resin containing dimethylaminododecyl methacrylate inhibits *Candida albicans* biofilm. *Materials* 2017; 10(4): 431.
<http://dx.doi.org/10.3390/ma10040431> PMID: 28772791
 - [33] Abdulrazzaq Naji S, Jafarzadeh Kashi TS, Pourhajibagher M, Behroozibakhsh M, Masaeli R, Bahador A. Evaluation of antimicrobial properties of conventional polymethyl methacrylate denture base resin materials containing hydrothermally synthesized anatase TiO2 nanotubes against cariogenic bacteria and *Candida albicans*. *Iran J Pharm Res* 2018; 17(Suppl. 2): 161-72.
PMID: 31011350
 - [34] Altaie SF. Tribological, microhardness and color stability properties of a heat-cured acrylic resin denture base after reinforcement with different types of nanofiller particles. *Dent Med Probl* 2023; 60(2): 295-302.
<http://dx.doi.org/10.17219/dmp/137611> PMID: 37260349
 - [35] Yaman ÇK, Demir N, Arslan U, Çiftçi N. Antimicrobial, optical, and mechanical properties of saliva-contaminated silver-zeolite nanoparticle-incorporated dental acrylic resins. *Inorganics* 2024; 12(10): 258.
<http://dx.doi.org/10.3390/inorganics12100258>
 - [36] Taymour N, Haque MA, Atia GAN, *et al.* Nanodiamond: A promising carbon-based nanomaterial for therapeutic and regenerative dental applications. *ChemistrySelect* 2024; 9(35): e202401328.
<http://dx.doi.org/10.1002/slct.202401328>
 - [37] AlHamdan EM. Influence of contemporary photoactivated disinfection on the mechanical properties and antimicrobial activity of PMMA denture base: A systematic review and meta analysis. *Photodiagn Photodyn Ther* 2023; 42: 103523.
<http://dx.doi.org/10.1016/j.pdpdt.2023.103523> PMID: 36958538
 - [38] Rao MH, Rajkumar K, Pavithra G, *et al.* Antibiofilm efficiency of silver and copper nanoparticle incorporated calcium hydroxide as an intracanal medicament: An *in vitro* study. *J Oral Biol Craniofac Res* 2025; 15(2): 319-24.
<http://dx.doi.org/10.1016/j.jobcr.2025.01.020> PMID: 40027858
 - [39] Maldonado K, Xu D, Wang Y, *et al.* Mechanical and physical properties of experimental antifungal denture base resins. *Oral Health Dent Stud* 2018; 1(1): 5.
<http://dx.doi.org/10.31532/OralHealthDentStud.1.1.005>

DISCLAIMER: Please note that this article is currently in the 'Early view' stage and is not the final 'Version of Record'. While it has been accepted, copy-edited, and formatted, however, it is still undergoing proofreading and corrections by the authors. Therefore, the text may still change before the final publication. Although 'Early view' may not have all bibliographic details available, the DOI and the year of online publication can still be used to cite them. The article title, DOI, publication year, and author(s) should all be included in the citation format. Once the 'Final Version of Record' becomes available the 'Early view' will be replaced by that.