



The Open Dentistry Journal

Content list available at: <https://opendentistryjournal.com>



RESEARCH ARTICLE

Preparation and Evaluation of Chitosan Nanoparticles containing Iranian *Eschium Amoenum* Extract and its Antimicrobial Effects on Common Oral Microorganisms

Farshad Barzegar^{1,#}, Sepideh Bohlouli^{1,#}, Elaheh Fakhri^{2,#}, Solmaz Maleki Diza^{2,*}, Mohammad Yousef Memar³ and Fatemeh Sobhanifar¹

¹Department of Oral Medicine, Faculty of Dentistry, Tabriz University of Medical Sciences, Tabriz, Iran

²Dental and Periodontal Research Center, Tabriz University of Medical Sciences, Tabriz, Iran

³Infectious and Tropical Diseases Research Center, Tabriz University of Medical Sciences, Tabriz, Iran

Abstract:

Background and Aim:

Chitosan nanoparticles are one of the biocompatible and bioactive vectors in medicine contributing to the transfer and slow release of antimicrobial agents. The present study investigated loading *Echium amoenum* extract on chitosan nanoparticles and evaluated the antimicrobial effects of this composite on *Streptococcus mutans*, *Candida albicans*, and *Escherichia coli*.

Materials and Methods:

First, a chitosan solution was prepared in 1% acetic acid. Then, a tripolyphosphate (TPP) solution was added to it. The resulting mixture was centrifuged, and finally, its powder was dried. The *E. amoenum* extract was prepared and added to the chitosan powder. After mixing, the mixture was centrifuged, and the chitosan nanoparticle powder containing *E. amoenum* was separated and dried. The properties and characteristics of the nanoparticles were determined by the DLS test, and their stability was evaluated using the zeta potential. Finally, the antimicrobial effect of this product was evaluated on *S. mutans*, *E. coli*, and *C. albicans* using MIC and MBC through the microdilution method.

Results:

The sizes of chitosan nanoparticles and chitosan nanoparticles containing the plant extract were 98 ± 1.24 and 108 ± 1.54 nm and their zeta potentials were +17 and +10, respectively. The MIC for chitosan, the extract, and chitosan nanoparticles containing *E. amoenum* extract for *E. coli* were 170.67, 666.67, and 341.34 mg/mL; these values for *S. mutans* were 106.67, 416.67, and 170.67 mg/mL, with 426.67, 1000, and 341.34 mg/mL for *C. albicans*, respectively. The MBC for chitosan, the extract, and chitosan nanoparticles containing *E. amoenum* extract for *E. coli* were 426.67, 1666.67, and 853.34 mg/mL; these values for *S. mutans* were 426.67, 833.34, and 426.67 mg/mL, with 853.34, 1666.67, and 853.34 mg/mL for *C. albicans*, respectively.

Conclusion:

Chitosan nanoparticles are an efficient vector for *E. amoenum* extract and loaded chitosan nanoparticles can be used as a bioactive antibacterial agent against various oral microorganisms.

Keywords: *Candida albicans*, Chitosan, *Escherichia coli*, *Echium amoenum* extract, Nanoparticles, Oral microorganisms, *Streptococcus mutans*.

Article History

Received: July 09, 2023

Revised: September 03, 2023

Accepted: September 26, 2023

1. INTRODUCTION

The oral environment can be considered a haven for many pathogenic and opportunistic microorganisms due to its continuous relationship with the external environment. Recent investigations have identified >1000 microbial species in the

oral cavity [1], colonization of which, increases the chances of their penetration into the other body tissues, resulting in the development of systemic diseases [2]. *Streptococcus mutans* is a facultative anaerobic gram-positive bacterial species and a member of the oral microbiome. Due to its acidogenic and aciduric properties, it is the most pathogenic bacteria for caries and root canal infections. This bacterial species can form biofilms, known as dental plaque [3].

* Address correspondence to this author at the Dental and Periodontal Research Center, Tabriz University of Medical Sciences, Tabriz, Iran;
E-mail: maleki.s.89@gmail.com

#These authors contributed equally to this work

Candida albicans is a fungal species commonly found in oral infections comprising up to 75% of fungal species in the oral cavity [4]. The virulence factors of *C. albicans* include the ability to change its morphology, strong adhesion to porous surfaces and cells, thigmotropism, and the ability to secrete hydrolytic enzymes, such as protease, phospholipases, and lipases [1, 5].

Escherichia coli is a facultative anaerobic gram-negative bacterial species primarily identified in the digestive tract. *E. coli* has also been identified in various oral and root canal infections [6].

The emergence of antibiotic-resistant bacteria has precipitated a growing health crisis which is compelling researchers towards alternative methods with both antibacterial activity and minimum side effects for human beings [7]. Many studies have evaluated the antibacterial properties of medicinal plants [8, 9]. An important medicinal plant in Iranian traditional medicine is the species of *Echium*, especially *Echium amoenum* (from the *Boraginaceae* family), due to its medicinal and nutritional properties [9]. This plant's extract contains flavonoids, saponins, unsaturated terpenoids, and sterols. Phytochemical studies on *E. amoenum* have shown the presence of many chemical agents, such as RA, anthocyanidin, flavonoids, g-linolenic acid, and small amounts of alkaloids [8, 10]. The antioxidative and antimicrobial properties of flavonoids and RA are well-established [11].

Previous studies have evaluated the antimicrobial effects of *E. amoenum* against *Staphylococcus aureus* using agar diffusion and microdilution methods. The minimum concentration of *E. amoenum* that inhibits the growth of *S. aureus* (MIC) has been reported to be 6.2 µg/mL [12]. Another study evaluated the antimicrobial effect of *E. amoenum* seed oil against *S. aureus*, *C. albicans*, and *Pseudomonas aeruginosa*. The results showed that the seed oil of *E. amoenum* did not affect *S. aureus*; however, it significantly decreased *C. albicans* and *P. aeruginosa* [13].

Chitosan-based drug delivery systems are used to carry and deliver anti-inflammatory, antibacterial (different antibiotics), antioxidative and anti-cancer agents [14]. Nanoparticles (NPs) prepared from chitosan derivatives usually have a positive surface charge and mucous-adhesion properties, so they can adhere to mucous membranes and release their drug loads consistently [15]. Several studies have evaluated chitosan NPs to carry different antibiotics, polyphenol products, [16, 17] and plant extracts such as *Mentha longifolia* [18], *Arrabidaea chica* [19], *Scutellaria baicalensis* [20] and *Ginkgo Biloba* [21]. Producing chitosan NPs using TPP as a crosslinker is an efficient and safe method. Particles are made by electrostatic interactions between amine groups of chitosan and phosphate groups of TPP. It has been reported that addition of TPP results in lower particle size, improved loading efficiency, cellular uptake and better bioactivity [22].

Given the appearance of bacterial species resistant to antibiotics and the side effects of these compounds, attempts to achieve alternative materials using herbal compounds or natural polymers have increased. In addition, the next step to take is to load the target agent in bioactive nanocarriers to

achieve a persistent slow release. Although previous studies demonstrated the antibacterial activity of *E. amoenum*, the present study evaluated the effect of loading *E. amoenum* on chitosan NPs and its slow release to control oral microorganisms, so an alternative could be introduced for currently available mouthwashes and antimicrobial agents.

2. MATERIALS AND METHODS

In the present *in vitro* study, standard strains of *S. mutans* (ATCC 25175) and *E. coli* (ATCC 25922) from the microbial bank of Iran Pasteur Institute were prepared and cultured on a blood agar solid medium. In addition, *C. albicans* fungal species (ATCC 10231) was incubated in Sabouraud dextrose agar medium for 24 hours. MIC (minimum inhibitory concentration) test was performed using the microdilution method to evaluate the antimicrobial properties and minimum inhibitory concentration of the above-mentioned nanoparticles. To this end, the microorganisms were cultured in the tryptic soy broth (TBS) medium at 37°C for 24 hours. The next day, McFarland's 0.5 concentration, equal to 1.5×10^8 CFU/mL was prepared. Different concentrations of the chitosan NPs containing the extract were prepared to evaluate their effects. Different concentrations of the material were added to special microtiter plates. In addition, two wells were allocated to chitosan and *E. amoenum* extract alone. One well that contained the culture medium and the evaluated material (without bacteria) was considered the negative control. Then the microbial suspension was added to the wells and incubated in the presence of CO₂ at 37°C for 24 hours. MIC is the minimum concentration of the material that presents the formation of colonies on the culture medium surface.

To determine MBC (minimum bacterial concentration), 10 µL of the solution was removed from the wells with no microorganism growth and cultured in the agar medium. Finally, the plates were incubated, and the formed colonies were counted. MBC is the minimum concentration of the material that prevents colony formation on the culture medium surface [23, 24].

2.1. Preparation of Chitosan Nanoparticles

The ionic gelation method was used to prepare chitosan NPs, in which chitosan solution was prepared at a concentration of 1 mg/mL in 1 wt% of acetic acid. This solution was placed on a stirrer until a completely clear solution was achieved with no undissolved particles. Tripolyphosphate solution was prepared with 1 mg/mL concentration in distilled water and added to the chitosan solution. After completing the reaction, to separate the NPs, the suspension was centrifuged at 20000 rpm for 10 minutes. To eliminate impurities, the sample was rinsed with distilled water and centrifuged again. The achieved nanoparticle powder was dried and used [25].

2.2. Loading *E. Amoenum* Extract in Chitosan

E. amoenum extract was procured, and its aqueous solution [1 mg/mL] was prepared. Then this solution was mixed with 20 mg/mL of NPs. The mixing procedure continued on a stirrer for 24 hours. Then the NPs containing the extract were

centrifuged at 10000 rpm. Then the NPs were rinsed with distilled water and centrifuged again. The resulting powder was dried and used.

2.3. Evaluation of the Properties and Characteristics of Chitosan NPs Containing *E. Amoenum* Extract

The particle size distribution graph was drawn using the laser diffraction method to compare the sizes of chitosan NPs prepared from the initial chitosan sample. The NP sizes were determined using the DLS [dynamic light scattering] method. In addition, the zeta potential was evaluated to determine the stability of NPs.

3. RESULTS

3.1. Characterization of Nanoparticles

According to the DLS test, the NP sizes of chitosan and chitosan containing *E .amoenum* extract were 98 ± 1.24 and 108 ± 1.54 nm, respectively (Figs. 1 and 2). The polydispersity index for chitosan NPs and chitosan NPs containing *E. amoenum* extract were 0.3 and 0.4, respectively. The zeta potential of chitosan NPs and chitosan NPs containing *E. amoenum* extract were +17 and +10 mV, respectively, according to the same test (Figs. 3 and 4).




Fig. (1). The size distribution of chitosan NPs.




Fig. (2). The size distribution of chitosan NPs containing *E. amoenum* extract.




Fig. (3). The zeta potential of chitosan NPs.




Fig. (4). The zeta potential of chitosan NPs containing *E. amomum* extract.




Fig. (5). The MBC and MIC values of chitosan NPs, *E. amoenum* extract, and chitosan nanoparticles containing *E. amoenum* extract.

3.2. Antibacterial Activity

The MICs for chitosan, *E. amoenum* extract, and chitosan NPs containing *E. amoenum* extract against *E. coli* were 170.67, 666.67, and 341.34 mg/mL, respectively. These values for *S. mutans* were 106.67, 416.67, and 170.67 mg/mL, with 426.67, 1000, and 341.34 mg/mL for *C. albicans*, respectively (Fig. 5). The MBCs for chitosan, the extract, and chitosan nanoparticles containing *E. amoenum* extract for *E. coli* were 426.67, 1666.67, and 843.34 mg/mL, respectively. These values for *S. mutans* were 426.67, 833.34, and 426.67 mg/mL, with 853.34, 1666.67, and 853.34 mg/mL for *C. albicans*, respectively (Fig. 5).

4. DISCUSSION

The present study evaluated the antimicrobial properties of chitosan, *E. amoenum* extract, and chitosan nanoparticles containing *E. amoenum* extract against *S. mutans*, *C. albicans*, and *E. coli* as the most commonly found bacterial and fungal

species in the oral cavity [1]. The results show that the MIC and MBC values of chitosan NPs containing *E. amoenum* extract are less than the MIC and MBC values of *E. amoenum* extract alone against all tested pathogens. The decrease in MIC and MBC against microorganisms of the *E. amoenum* extract after loading on chitosan NPs is due to the synergistic antimicrobial effect of chitosan. In addition, NPs have a larger surface area for contact with cells and bacteria due to their smaller size and larger total surface area, increasing the bioactivity of medications loaded on NPs [26]. A study by Farmoudeh *et al.* showed that loading ginger extract on chitosan NPs decreased MBC and MIC against different microorganisms [27]. Consistent with the present study, Bagheri *et al.* showed that loading nettle [urtica] extract on chitosan NPs produced using the ionic gelation method improved the antibacterial properties of this compound against *E. coli* and *S. aureus* [28].

Previous studies have attributed the antimicrobial

properties of *E. amoenum* extract to its phenolic compounds. The antimicrobial effect of this extract is dose-dependent, and its effect increases with an increase in concentration and its release from the vector [29]. In the present study, the minimum concentration required for inhibiting *E. coli* was higher than that for *S. mutans*, which might be explained by differences in the bacterial wall between gram-negative [*E. coli*] and gram-positive [*S. mutans*] bacteria, making the antibacterial agents less effective on gram-negative bacteria [30].

Previous studies have evaluated the antibacterial effect of *E. amoenum* extract on *S. aureus* using agar diffusion and microdilution methods. A previous study reported an MIC of 6.2 mg/mL to inhibit *S. aureus* [12]. Bonjar *et al.* evaluated the antimicrobial effect of *E. amoenum* extract on *Bordetella bronchiseptica* and *Klebsiella pneumoniae* using the disc diffusion method and reported an MIC of 15 µg/mL for the methanolic extract of *E. amoenum* [31]. Another study showed that the seed oil of *E. amoenum* had no effect on *S. aureus* but significantly decreased *C. albicans* and *P. aeruginosa* counts [13]. All these studies have shown the antibacterial and antifungal activity of *E. amoenum* extract, consistent with the present study.

In the present study, the *E. amoenum* extract was loaded on chitosan NPs, and its properties were evaluated using the ionic gelation method, which can be implemented in an aqueous environment and does not lead to new toxic chemical bonds in the chitosan structure [32].

In the present study, the chitosan NP dimension was 98 nm. Previous studies have shown that 10–100-nm NPs are suitable for carrying and delivering medicines because NPs with larger sizes might not penetrate the target cells and might accumulate in vital organs such as the liver and kidneys [26]. In addition, in the present study, the particle distribution index [PDI] was 0.3, indicating uniform NP sizes.

A previous study by Fan *et al.* (2012) showed that preparing chitosan NPs using the ionic gelatin method leads to the production of NPs with high stability with a diameter of about 138 nm, with the help of TPP as a cross-linking material [33]. In the present study, the chitosan NP size was 98 nm. In addition, the present study showed that with this method, the stability of chitosan NPs was favorable at room temperature for up to 20 days; *i.e.*, the dimensions and distribution of NPs did not change significantly during this period.

Vaezifar *et al.* (2013), too, used the ionic gelation method and TPP anion to prepare chitosan NPs. They reported that the dimensions of the NPs produced using this method depended on the initial concentration of chitosan, the concentration of TPP, and the duration of the reaction. The optimal factors reported in this study were 1 mg/mL, 1 mg/mL, and 60 minutes, respectively [34]. Since the parameters of the ionic gelation method in the present study were consistent with those in the study by Vaezifar *et al.*, the NP dimensions in the present study were consistent with that study, *i.e.*, NP dimensions were <200 nm in both studies.

Neves *et al.*, too, (2014) used this method to produce chitosan NPs and showed that the NPs' zeta potential increased with an increase in chitosan concentration, which might be

attributed to an increase in NH³⁺ groups [35]. The zeta potential shows the electrostatic resistance between the particles and is mostly used as an index to evaluate the distribution stability of the sample. A high zeta potential indicates that the suspension is in a favorable state regarding electrostatic stability. In addition, this parameter affects the amount and rate of medication release from the NPs and the interaction between the medication and the cell. The zeta potential of chitosan NPs in this study was +17 mV, indicating the stability of the compound. However, loading the extract decreased this stability to +10 mV [36]. The type of material loaded on chitosan NPs affects its stability and zeta potential. For example, Du *et al.* showed that loading metallic ions [with a positive charge] increased the zeta potential of chitosan NPs [37]. A decrease in zeta potential after loading *E. amoenum* extract was due to phenolic components in this extract. However, a positive zeta potential facilitates the interaction between the NPs and the cell membranes for the absorption and release of medications and with bacterial walls to destroy bacteria [38]. Loading the *E. amoenum* extract slightly increased NP sizes [108 nm], consistent with previous studies. Bagheri *et al.*, too, (2021) produced chitosan NPs using the ionic gelatin method. The dimension of these NPs was 208 nm before loading, which increased to 369 nm after loading nettle oil [28]. In this line, Keawchaon *et al.* (2011) loaded the phenolic compound carvacrol on chitosan NPs. An increase in carvacrol concentration increased the dimension of chitosan NPs and decreased the zeta potential [39]. In addition, loading clove extract on chitosan NPs in a study by Hadidi *et al.* (2020) increased the NP dimension from 223 to 444 nm and decreased the zeta potential [40].

In summary, chitosan NPs in the present study produced using the ionic gelatin method, presented acceptable characteristics and addition of *E. amoenum* extract to chitosan NPs demonstrated a synergistic antibacterial and antifungal effect against common oral microorganisms. However, wider studies on cytotoxicity and biofilm cultures are needed previous to bringing the produced compound to the clinical evaluations. One of the future aims of the present study is to use chitosan NPs containing *E. amoenum* extract to prepare mouthwashes against dental caries or fungal diseases or prepare intracanal medications for radicular infections or placement in periodontal pockets to treat periodontitis.

CONCLUSION

Chitosan NPs containing *E. amoenum* extract produced by ionic gelation method demonstrated a synergistic effect resulting in elimination of the common oral bacteria and fungi. Considering the structural properties of chitosan NPs as a natural polymer, they can be used as a proper and safe vector for medications and extracts with antibacterial and antifungal properties for oral microorganisms.

LIST OF ABBREVIATIONS

TPP	=	Tripolyphosphate
TBS	=	Tryptic Soy Broth

ETHICS APPROVAL AND CONSENT TO PARTICIPATE

The project was found to be in accordance with the ethical principles and the national norms and standards for conducting

Medical Research with an Ethics code of IR.TBZMED.VCR.REC.1401.125 from the ethics committee of Tabriz University of Medical Sciences.

HUMAN AND ANIMAL RIGHTS

No animals/humans were used in this research.

CONSENT FOR PUBLICATION

Not applicable.

AVAILABILITY OF DATA AND MATERIALS

The raw/processed data required to reproduce these findings can be shared after publication by requesting from the corresponding author [S.D].

FUNDING

This study has been funded by the Vice-Chancellor for Research (VCR) of Tabriz University of Medical Sciences.

CONFLICT OF INTEREST

Dr. Solmaz Maleki Dizaj is on the Editorial Advisory Board of the journal *The Open Dentistry Journal*.

ACKNOWLEDGMENTS

This study was based on a thesis [No. 69924] registered at the Faculty of Dentistry, Tabriz University of Medical Sciences, Tabriz, Iran. It was financially supported by the Vice-Chancellor for Research at Tabriz University of Medical Sciences, Tabriz, Iran which is greatly acknowledged.

REFERENCES

- Dewhirst FE, Chen T, Izard J, et al. The human oral microbiome. *J Bacteriol* 2010; 192(19): 5002-17. [http://dx.doi.org/10.1128/JB.00542-10] [PMID: 20656903]
- Wade WG. The oral microbiome in health and disease. *Pharmacol Res* 2013; 69(1): 137-43. [http://dx.doi.org/10.1016/j.phrs.2012.11.006] [PMID: 23201354]
- Hamada S, Slade HD. Biology, immunology, and cariogenicity of *Streptococcus mutans*. *Microbiol Rev* 1980; 44(2): 331-84. [http://dx.doi.org/10.1128/mr.44.2.331-384.1980] [PMID: 6446023]
- Sudbery P, Gow N, Berman J. The distinct morphogenic states of *Candida albicans*. *Trends Microbiol* 2004; 12(7): 317-24. [http://dx.doi.org/10.1016/j.tim.2004.05.008] [PMID: 15223059]
- Costa-de-Oliveira S, Rodrigues AG. *Candida albicans* antifungal resistance and tolerance in bloodstream infections: The triad yeast-host-antifungal. *Microorganisms* 2020; 8(2): 154. [http://dx.doi.org/10.3390/microorganisms8020154] [PMID: 31979032]
- Lai CC, Huang FM, Yang HW, et al. Antimicrobial activity of four root canal sealers against endodontic pathogens. *Clin Oral Investig* 2001; 5(4): 236-9. [http://dx.doi.org/10.1007/s00784-001-0135-2] [PMID: 11800436]
- Levy SB, Marshall B. Antibacterial resistance worldwide: Causes, challenges and responses. *Nat Med* 2004; 10(S12): S122-9. [http://dx.doi.org/10.1038/nm1145] [PMID: 15577930]
- Azizi H, Ghafari S, Ghods R, Shojaii A, Salmanian M, Ghafarzadeh J. A review study on pharmacological activities, chemical constituents, and traditional uses of *Echium amoenum*. *Pharmacogn Rev* 2018; 12(24)
- Miraj S, Kiani S. A review study of therapeutic effects of Iranian borage (*Echium amoenum* Fisch). *Pharm Lett* 2016; 8(6): 102-9.
- Adel Pilerood S, Prakash J. Evaluation of nutritional composition and antioxidant activity of Borage (*Echium amoenum*) and Valerian (*Valeriana officinalis*). *J Food Sci Technol* 2014; 51(5): 845-54. [http://dx.doi.org/10.1007/s13197-011-0573-z] [PMID: 24803690]
- Abed A, Vaseghi G, Jafari E, Fattahian E, Babhadiashar N, Abed M. *Echium amoenum* fish. Et Mey: A review on its pharmacological and medicinal properties. *Asian J Med Pharm Res* 2014; 4: 21-3.
- Mansouri S. Inhibition of *Staphylococcus aureus* mediated by extracts from Iranian plants. *Pharm Biol* 1999; 37(5): 375-7. [http://dx.doi.org/10.1076/phbi.37.5.375.6058]
- Hamed J, Vatani M. Antibacterial and antifungal effects of evening primrose "*Oenothera biennis* L." and Borage "*Echium amoenum* Fisch. & C.A.Mey. oils. *Nova Biologica Reperta* 2015; 2(3): 199-206.
- Prabaharan M, Mano JF. Chitosan-based particles as controlled drug delivery systems. *Drug Deliv* 2004; 12(1): 41-57. [http://dx.doi.org/10.1080/10717540590889781] [PMID: 15801720]
- Ali A, Ahmed S. A review on chitosan and its nanocomposites in drug delivery. *Int J Biol Macromol* 2018; 109: 273-86. [http://dx.doi.org/10.1016/j.ijbiomac.2017.12.078] [PMID: 29248555]
- Bhatia A, Shard P, Chopra D, Mishra T. Chitosan nanoparticles as carrier of immunorestoratory plant extract: Synthesis, characterization and immunorestoratory efficacy. *Int J Drug Deliv* 2011; 3(2): 381.
- Gupta DK, Kesharwani S, Sharma N, Gupta MK. Formulation and evaluation of herbal extract of *allivum sativum* (garlic) loaded chitosan nanoparticles. *J Drug Deliv Ther* 2019; 9(3-s): 715-8.
- El-Aziz ARMA, Al-Othman MR, Mahmoud MA, Shehata SM, Abdelazim NS. Chitosan nanoparticles as a carrier for *Mentha longifolia* extract: Synthesis, characterization and antifungal activity. *Curr Sci* 2018; 2116-22.
- Servat-Medina L, González-Gómez A, Reyes-Ortega F, et al. Chitosan-tripolyphosphate nanoparticles as *Arrabidaea chica* standardized extract carrier: synthesis, characterization, biocompatibility, and antiulcerogenic activity. *Int J Nanomedicine* 2015; 10: 3897-909. [http://dx.doi.org/10.2147/IJN.S83705] [PMID: 26089666]
- Paczkowska-Walendowska M, Cielecka-Piontek J. Chitosan as a functional carrier for the local delivery anti-inflammatory systems containing *scutellariae baicalensis radix* extract. *Pharmaceutics* 2022; 14(10): 2148. [http://dx.doi.org/10.3390/pharmaceutics14102148] [PMID: 36297583]
- Karavelioglu Z, Cakir-Koc R. Preparation of chitosan nanoparticles as Ginkgo Biloba extract carrier: *in vitro* neuroprotective effect on oxidative stress-induced human neuroblastoma cells (SH-SY5Y). *Int J Biol Macromol* 2021; 192: 675-83. [http://dx.doi.org/10.1016/j.ijbiomac.2021.10.023] [PMID: 34655582]
- Pan C, Qian J, Zhao C, Yang H, Zhao X, Guo H. Study on the relationship between crosslinking degree and properties of TPP crosslinked chitosan nanoparticles. *Carbohydr Polym* 2020; 241: 116349. [http://dx.doi.org/10.1016/j.carbpol.2020.116349] [PMID: 32507176]
- Fakhri E, Samadi Kafil H, Naghizadeh M, Eslami H, Sefidan FY. Antimicrobial effect of grape seed extract as a potential intracanal medicament combined with Nd: YAG laser. *Aust Endod J* 2022; 49(1): 209-16. [PMID: 36479792]
- Watts JL, Shryock T, Apley M, Bade D, Brown S, Gray J. Performance standards for antimicrobial disk and dilution susceptibility tests for bacteria isolated from animals. *Clinical and laboratory standards institute* 2008.
- Gan Q, Wang T, Cochrane C, McCarron P. Modulation of surface charge, particle size and morphological properties of chitosan-TTP nanoparticles intended for gene delivery. *Colloids Surf B Biointerfaces* 2005; 44(2-3): 65-73. [http://dx.doi.org/10.1016/j.colsurfb.2005.06.001] [PMID: 16024239]
- Blanco E, Shen H, Ferrari M. Principles of nanoparticle design for overcoming biological barriers to drug delivery. *Nat Biotechnol* 2015; 33(9): 941-51. [http://dx.doi.org/10.1038/nbt.3330] [PMID: 26348965]
- Farmoudeh A, Shokoochi A, Ebrahimnejad P. Preparation and evaluation of the antibacterial effect of chitosan nanoparticles containing ginger extract tailored by central composite design. *Adv Pharm Bull* 2020; 11(4): 643-50. [http://dx.doi.org/10.34172/apb.2021.073] [PMID: 34888211]
- Bagheri R, Ariaei P, Motamedzadegan A. Characterization, antioxidant and antibacterial activities of chitosan nanoparticles loaded with nettle essential oil. *J Food Meas Charact* 2021; 15(2): 1395-402. [http://dx.doi.org/10.1007/s11694-020-00738-0]
- Mehrabani M, Ghassemi N, Ghannadi ESA, Shams-Ardakani M. Main phenolic compound of petals of *Echium amoenum* Fisch. and CA Mey., A famous medicinal plant of Iran. *Daru* 2005; 13(2): 65-9.

- [30] Vasoo S, Barreto JN, Tosh PK, Eds. Emerging issues in gram-negative bacterial resistance: An update for the practicing clinician Mayo Clinic Proceedings. Elsevier 2015.
[<http://dx.doi.org/10.1016/j.mayocp.2014.12.002>]
- [31] Bonjar GS. Evaluation of antibacterial properties of Iranian medicinal-plants against *Micrococcus luteus*, *Serratia marcescens*, *Klebsiella pneumoniae* and *Bordetella bronchoseptica*. Asian J Plant Sci 2004.
- [32] Sadeghi M, Ganji F, Taghizadeh SM. Preparation and optimization of labeled chitosan nanoparticles and evaluation of their release from transdermal drug delivery system. Iran J Polym Sci Technol 2015; 28(4): 344-3.
- [33] Fan W, Yan W, Xu Z, Ni H. Formation mechanism of monodisperse, low molecular weight chitosan nanoparticles by ionic gelation technique. Colloids Surf B Biointerfaces 2012; 90: 21-7.
[<http://dx.doi.org/10.1016/j.colsurfb.2011.09.042>] [PMID: 22014934]
- [34] Vaezifar S, Razavi S, Golozar MA, Karbasi S, Morshed M, Kamali M. Effects of some parameters on particle size distribution of chitosan nanoparticles prepared by ionic gelation method. J Cluster Sci 2013; 24(3): 891-903.
[<http://dx.doi.org/10.1007/s10876-013-0583-2>]
- [35] de Pinho Neves AL, Milioli CC, Müller L, Riella HG, Kuhnen NC, Stulzer HK. Factorial design as tool in chitosan nanoparticles development by ionic gelation technique. Colloids Surf A Physicochem Eng Asp 2014; 445: 34-9.
[<http://dx.doi.org/10.1016/j.colsurfa.2013.12.058>]
- [36] Xu R. Progress in nanoparticles characterization: Sizing and zeta potential measurement. Particuology 2008; 6(2): 112-5.
[<http://dx.doi.org/10.1016/j.partic.2007.12.002>]
- [37] Du WL, Niu SS, Xu YL, Xu ZR, Fan CL. Antibacterial activity of chitosan tripolyphosphate nanoparticles loaded with various metal ions. Carbohydr Polym 2009; 75(3): 385-9.
[<http://dx.doi.org/10.1016/j.carbpol.2008.07.039>]
- [38] Madureira AR, Pereira A, Pintado M. Current state on the development of nanoparticles for use against bacterial gastrointestinal pathogens. Focus on chitosan nanoparticles loaded with phenolic compounds. Carbohydr Polym 2015; 130: 429-39.
[<http://dx.doi.org/10.1016/j.carbpol.2015.05.030>] [PMID: 26076644]
- [39] Keawchaon L, Yoksan R. Preparation, characterization and *in vitro* release study of carvacrol-loaded chitosan nanoparticles. Colloids Surf B Biointerfaces 2011; 84(1): 163-71.
[<http://dx.doi.org/10.1016/j.colsurfb.2010.12.031>] [PMID: 21296562]
- [40] Hadidi M, Pouramin S, Adinepour F, Haghani S, Jafari SM. Chitosan nanoparticles loaded with clove essential oil: Characterization, antioxidant and antibacterial activities. Carbohydr Polym 2020; 236: 116075.
[<http://dx.doi.org/10.1016/j.carbpol.2020.116075>] [PMID: 32172888]

